

PAT-NO: JP360260427A  
DOCUMENT- JP 60260427 A  
IDENTIFIER:  
TITLE: VESSEL FOR SYNTHESIZING POSITIVE ELECTRODE  
ACTIVATING SUBSTANCE FOR CELL

PUBN-DATE: December 23, 1985

INVENTOR-INFORMATION:

NAME	COUNTRY
------	---------

EDA, NOBUO

FUJII, TAKAFUMI

MORITA, TERUYOSHI

KOSHINA, HIDE

MURAKAMI, KAORU

ASSIGNEE-INFORMATION:

NAME	COUNTRY
------	---------

MATSUSHITA ELECTRIC IND CO LTD N/A

APPL-NO: JP59115029

APPL-DATE: June 5, 1984

INT-CL (IPC): C01G049/00 , H01M004/58

US-CL-CURRENT: 422/50

ABSTRACT:

PURPOSE: To synthesize uniform CuFeS<sub>2</sub> when Cu<sub>2</sub>S and FeS<sub>2</sub> are heated in an inert gaseous atmosphere to synthesize CuFeS<sub>2</sub> as a positive electrode activating substance for a cell contg. an org. electrolytic soln., by using the vessel of a specified shape in synthesis.

CONSTITUTION: When CuFeS<sub>2</sub> as a positive electrode activating substance for a cell contg. an org. electrolytic soln. is synthesized

from Cu<sub>2</sub>S and FeS<sub>2</sub>, 2mol FeS<sub>2</sub> is well mixed with 1mol Cu<sub>2</sub>S, charged into a synthesizing vessel, and heated to 600–700°C in an inert gaseous atmosphere to synthesize the desired CuFeS<sub>2</sub>. At this time, an inverted trapezoidal or bowl-shaped vessel inclined gently at 30–60° angle at the side part is used as the synthesizing vessel. Eliminated gaseous sulfur generated during the synthesis reaction separates easily from the reaction product, and synthetic CuFeS<sub>2</sub> having a uniform composition is obtd. without leaving unreacted starting materials.

COPYRIGHT: (C)1985,JPO&Japio